




TOP VIEW



SIDE VIEW





BOTTOM VIEW



PREFORM
THIXOTROPIC LATENT
CURE ADHESIVE

Notes: (Unless Otherwise Specified).

- 1) MATERIAL:
 - A) LID: BLACK = PLASTIC BT.
 - B) PREFORM: LCA3000X LATENT CURE ADHESIVE.
- 2) RECOMENDED CURE:
 - BAKE AT 150°C FOR 60 MINUTES(MINIMUM)
 - WITH PRESSURE 1/2-LBS PER SQUARE INCH.
- 3) STORAGE LIFE: 12 MONTHS @ 25 °C, 24 MONTHS @ 0 °C.
- 4) THAW IF FROZEN: 8 HOURS (MIN) @ 25 °C BEFORE USE.

TOLERANCE UNLESS NOTED		APPROVALS		DATE	 Mirror Semiconductor™							
X.X	+/- 0.3	DRAWN J. Hines		11/27/2011					TITLE B-LID 6X6mm LID WITH PREFORM ADHESIVE			
X.XX	+/- 0.03	ENG										
X.XXX	+/- 0.003	MFG			SCALE 15:1		SIZE A		DRAWING NO. 206103		REV A	
ANGLES +/- 0.5° ALL DIMENSIONS IN <input checked="" type="checkbox"/> INCHES <input checked="" type="checkbox"/> MILLIMETERS		THIRD ANGLE PROJECTION 		QA CUST REVISED								